

ZINC-ALUMINIUM SPRAY

Suitable for long-lasting corrosion protection for all metals which are exposed to corrosive effects such as wheel rims. Also be used for priming plant, machine and body parts in the automotive, marine, construction and agricultural machinery sectors as well as industry and handicraft.

CHARACTERISTICS

- compatible with all sorts of material
- resistant to water, salt water, as well as weak acids and bases
- quick-drying, smooth, non-porous film

TECHNICAL DATA

colour	silver (matt)
temperature resistance	+200°C (sometimes up to +300°C)
processing temperature	+10°C to +25°C
shelf life	36 months; store in a cool and dry place

INSTRUCTIONS FOR USE

Processing Temperature: +10°C to +25°C. Shake can well before use. Free surfaces from coarse residues (e.g. sandblasting) and thoroughly clean and degrease with PETEC Multi Cleaner (Art. no. 82100 or 82200). Apply PETEC Zinc-Aluminium spray uniformly from a distance of approx. 20 cm on the surface to be coated. After approx. 8 minutes, the surface becomes dry, and after 20 to 30 minutes, it becomes firm to the touch. The entire drying process lasts 24 hours. Coatings should only be applied using suitable products, and once the surface has fully cured. Paints, varnishes or other media containing solvents may inhibit or ruin the curing process. Always carry out tests in order to ensure the suitability of the product for the application in question.

Observe the safety and technical datasheet! (Download PETEC data sheets from www.petec.de)

CONTAINER SIZE



Item-No. 71050

500 ml spray